## **TEST REPORT**

No. : XMIN190100111CCM Date : Jan.22, 2019 Page: 1 of 2

| Sample Name | : | L'FLOOR CARPET WHITE              |
|-------------|---|-----------------------------------|
| Material    | : | PVC COATED POLYESTER WOVEN FABRIC |
| Spec        | : | 85% PVC AND 15 POLYESTER          |

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

| *****              |   |  |  |  |  |  |
|--------------------|---|--|--|--|--|--|
| Test Required      | : | Selected test(s) as requested by applicant   |  |  |  |  |
| Date of Receipt    | : | Jan.16, 2019   |  |  |  |  |
| Testing Start Date | : | Jan.16, 2019   |  |  |  |  |
| Testing End Date   | : | Jan.22, 2019   |  |  |  |  |
| Test Result(s)     | : | For further details, please refer to the following page(s)<br>(Unless otherwise stated the results shown in this test report refer only to the<br>sample(s) tested)<br>******** To be continued******* |  |  |  |  |

Signed for SGS-CSTC Standards Technical Services Co., Ltd. Xiamen Branch Testing Center

Civi Huang Authorized Signatory

# **TEST REPORT**

No. : XMIN190100111CCM Date : Jan.22, 2019 Page: 2 of 2

Slip resistance (oil-wet ramp test)

#### Test Method:

DIN 51130:2014-02 Testing of floor coverings - Determination of the anti-slip property - Workrooms and fields of activities with slip danger, walking method - Ramp test

#### Sample Description:

Floor,1300mm×700mm, 1pc,see the photo(s)


### Test Result:

Testing direction& testing surface: see the photo(s)

| Test item(s)                        | Test result(s)                     | Classification |
|-------------------------------------|------------------------------------|----------------|
| Slip resistance (oil-wet ramp test) | Critical angle of inclination:7.8° | R9             |

#### Classification of oil-wet ramp test:

| Classification | Angle (degrees)             |
|----------------|-----------------------------|
| R9             | 6 <i>°</i> ≤X≤10°           |
| R10            | 10° <x≤19°< td=""></x≤19°<> |
| R11            | 19° <x≤27°< td=""></x≤27°<> |
| R12            | 27° <x≤35°< td=""></x≤35°<> |
| B13            | >35°                        |



Specimen photograph(s):

SGS authenticate the photo(s) on original report only \*\*\*\*\*\*\*\*End of report\*\*\*\*\*\*